



Silver release from nano-silver containing plastic food containers

Mackevica, Aiga; Olsson, Mikael Emil; Hansen, Steffen Foss

Publication date:
2014

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Mackevica, A., Olsson, M. E., & Hansen, S. F. (2014). *Silver release from nano-silver containing plastic food containers*. Poster session presented at Nanotech 2014, Washington DC, United States.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.



Sustainable Nanotechnologies Project

Silver release from nano-silver containing plastic food containers

Aiga Mackevica*, Mikael Emil Olsson and Steffen Foss Hansen
Technical University of Denmark, Department of Environmental Engineering
*aima@env.dtu.dk



Introduction / Materials & Methods

The potential migration of AgNP into food and during washing, scrubbing, etc. has been poorly addressed; however, it is essential for the purpose of human and environmental exposure assessment.

Experimental setup:

Migration assay was set up following European Commission Directive 97/48/EC for articles intended to be in contact with food.

Four brands of commercially available plastic food containers were incubated for 10 days at 40°C with three different food simulants: Milli-Q water, 10% ethanol, and 3% acetic acid.


Analysis:

The total amount of silver in plastic containers (day 0) and migration solutions (day 10) was quantified by ICP-MS analysis.


The size of the migrated particles was investigated by

- single particle ICP-MS (Agilent 7700x)
- TEM-EDS imaging (FEI Tecnai G2)

Results – total silver migration




Results – single particle ICP-MS



Results – single particle ICP-MS


Due to the dissolved silver the background peak is really broad making it difficult to obtain a good size distribution

Samples had very few particles (too dilute solutions) with great difference in sizes



Y axis truncated at 15 for size distribution graphs. Bin size = 10.
Background and size distribution calculations performed as described by Pace et al. (2011) *Analytical chemistry* 83.24: 9361-9369.

Results – TEM-EDS



- EDS spectra confirmed that particles found consisted of Ag
- Both dispersed and agglomerated particles were observed
- AgNP sizes were ranging from around 20 nm to more than 200 nm

Discussion / Conclusions

- Highest migration of total silver was observed in acetic acid for all four brands
- Single particle ICP-MS results showed that in acetic acid there was more dissolved silver found than particulate silver
- The presence of AgNP was confirmed by TEM-EDS analysis for all acetic acid samples
- The brand with highest release of Ag (ng/cm²) was Special Nanosilver Mother's milk pack from Jaco, Korea
- The highest content of Ag (per cm²) was measured for The Original Always Fresh Containers™

This project has received funding from the European Union's Seventh Framework Programme [FP7/2007-2013] under EC-GA No. 604305 'SUN'

